

# VITROPERM® 220

# VITROPERM® 250



## NOMINAL ALLOY COMPOSITION

Alloy	Fe	Ni	Co	Cu	Nb	Si	B	
VP 220	Balance (66.4)	11.6	8.1	1.0	5.3	5.9	1.7	(wt-%)
	60.5	10.1	7.0	0.8	2.9	10.7	8.0	(at.-%)
VP 250	Balance (74.2)	11.6	–	1.0	5.3	6.2	1.7	(wt-%)
	67.2	10.0	–	0.8	2.9	11.2	8.0	(at.-%)

## MAGNETIC PROPERTIES<sup>1</sup>

Property	VP 220	VP 250
Saturation polarization (as cast / amorphous @ 20 °C)	1.19 T	1.18 T
Saturation polarization (nanocrystalline @ 20 °C)	1.24 T	1.24 T
Saturation magnetostriction (as cast / amorphous)	25 ppm	23 ppm
Saturation magnetostriction (nanocrystalline)	10 - 11 ppm	8 - 9 ppm
Permeability (transverse field annealing ½ h @ 510 °C)	2,400	4,000
Permeability (transverse field annealing ½ h @ 530 °C)	2,000	3,200
Permeability (transverse field annealing ½ h @ 550 °C)	1,800	2,800
DC coercivity (F annealed / flat hysteresis loop)	> 5 A/m	> 3 A/m
Curie temperature	600 °C	600 °C

## PHYSICAL PROPERTIES<sup>1</sup>

Property	VP 220	VP 250
Mass density (as cast / amorphous)	7.42 g/cm <sup>3</sup>	7.35 g/cm <sup>3</sup>
Mass density (nanocrystalline)	7.62 g/cm <sup>3</sup>	7.55 g/cm <sup>3</sup>
Electrical resistivity	1.15 μΩm	1.15 μΩm
Coefficient of thermal expansion (20 - 100 °C)	8•10 <sup>-6</sup> /K	8•10 <sup>-6</sup> /K
Crystallization temperature	460 °C	480 °C

## AVAILABLE DIMENSIONS

Property	Value	Unit
Thickness (computed average thickness from weight)	20 ± 3	μm
Widths – slit to width (others on request)	2.0 ... 50.0 ± 0.25	mm
Widths – width as cast (others on request)	20.0 ... 54.5 ± 0.5	mm

<sup>1</sup> Typical values, not part of a specification

**VAC MAGNETICS LLC**

2935 Dolphin Drive  
Suite 103  
Elizabethtown, KY 42701  
Phone +1 270 769 1333  
Fax +1 270 769 3118  
info-usa@vacmagnetics.com

**VACUUMSCHMELZE CHINA MAGNETICS**

Shanghai Sales Office  
Room 06, 19F  
Zhongrong Hengrui International Plaza  
620 Zhangyang Road, Pudong District  
Shanghai, PRC 200122  
Phone +86 21 58 31 98 37  
Fax +86 21 58 31 99 37  
vac\_china@vacuumschmelze.com

**VACUUMSCHMELZE GMBH & CO. KG**

Grüner Weg 37  
D 63450 Hanau / Germany  
Phone +49 6181 380  
Fax +49 6181 382645  
info@vacuumschmelze.com  
www.vacuumschmelze.com

**VACUUMSCHMELZE SINGAPORE PTE LTD**

60, Paya Lebar Road  
Paya Lebar Square  
#06-16  
Singapore 409051  
Phone +65 6585 1243  
VACSingapore@vacuumschmelze.com

**OMG CHEMICALS & MAGNETICS PVT. LTD.****VACUUMSCHMELZE INDIA OFFICE**

A-101 & 102, Kailas Business Park  
Veer Savarkar Road  
Park Site  
Vikhroli West  
Mumbai-400079, Maharashtra  
Phone +91 22 2518 0017 / 0018  
vac\_india@vacuumschmelze.com

Published by VACUUMSCHMELZE GmbH & Co. KG, Hanau  
© VACUUMSCHMELZE GmbH & Co. KG 2019. All rights reserved.

® is a Registered Trademark of VACUUMSCHMELZE GmbH & Co. KG

Version: June 2019



**ADVANCED MATERIALS – THE KEY TO PROGRESS**